

Replacement Element Media

Dura-Life	
Appearance	White
Use	Filter bags
Composition	100% polyester
Area Weight (DIN 53854)	340 g/m ²
Thickness (DIN 53855)	1.6 mm
Air Permeability (DIN 53887)	170 l/dm ² min at 200 Pa
Dimensional Stability @ 177°C	<3.0%
Surface Finish	None
Additional Treatments	Heat set
Surface Electrical Resistance	Not applicable
BIA Category	Not applicable
Temperature (dry heat)	
Continuous	135°C
Peaks	150°C
Chemical Resistance	
Hydrolysis	Poor
Acids	Good
Alkalis	Good
Oxidising agents	Very Good
Organic solvents	Very Good
Abrasion Resistance	Very good
Supports Combustion	Yes
Application field	Dura-Life is suitable for the majority of temperature and chemical environments normally encountered in Dalumatic applications including acidic and weak alkaline conditions at ambient temperature.

Replacement Element Media



www.donaldson.com

Humberstone Lane
Thurmaston
Leicester LE4 8HP
England

Tel +44 (0)116 269 6161
Fax +44 (0)116 269 3028

Email: IFS-uk@emea.donaldson.com

Research Park Zone 1
Interleuvenlaan 1
B-3001 Leuven (Heverlee)
Belgium

Tel +32 (0)16 383 970
Fax +32 (0)16 383 938

Email: IFS-europe@emea.donaldson.com